


Trident Marine

Specifications



ORIGIN	Malaysia
CORE	Medang / Kelat
FACE/BACK	Meranti / Pink Kedondong
GRADE	B/BB
FINISH	Raw
SIZE	48" x 96"
VENEER CUT	Rotary Cut, WPF
VENEER THICKNESS	1.0mm
SURFACE SANDING	120-240 grit finish
GLUE TYPE	WBP EPA Certified
MOISTURE CONTENT	8%-12%
APPLICATIONS	Boats, ships, docks, baths, kitchens, decks, patios, porches



THICKNESS	# OF PLYS	THICKNESS VARIATION	SHEETS PER CRATE
12mm	7	11.5mm-12.5mm	78
18mm	9	17.5mm-18.5mm	52

TRIDENT MARINE FOLLOWS ALL GUIDELINES PER STANDARD GRADING BS 1088.

Based on availability, USply reserves the right to substitute product that may vary in species, core, country of origin, and/or other specifications.

Trident Marine

Standard Grading BS 1088


USply

NATURAL DEFECTS		
NUMBER	CATEGORY OF DEFECT	BB
1	Burls	Permitted
2	Pin Knots	Permitted
3	Live Knots	Permitted, 5 per m2 from face. Max dia. 25mm and not clustered
4	Knot Holes	Not Permitted
5	Color Variation	Permitted, not many
6	Stain/Mineral Streaks	Permitted, not many
7	Dry Pitch and Back Pocket	Permitted, Light 2 per m2, max width 4mm and max length 100mm, well filled
8	Wormholes, Pinholes, Worm Tracks	Permitted, small, no color change and not long, puttied
9	Vine Marks	Permitted, not many, lightly sanded and smooth
10	Joints	Permitted, max 3 joints, open width max 3mm and max length 10% of panels length and puttied
11	Splits-Open	Permitted
12	Splits - Filed or Puttied	Permitted, max 2 per panel on panel end, max width 5mm max length 8.5% of panel length, tight and color match
13	Fill or Putty Smears	Permitted, slight and smooth sanded
14	Rough Cut	Permitted, slight
15	Shims	Permitted, max 5mm, length 300mm, tight and color match
16	Knife Marks	Permitted, width 0.8mm and slight
17	Tape/Glue Residue	Permitted, slight and smooth sanded
18	Sanding	Permitted, slight
19	Chicken Tracks	Permitted

Based on availability, USply reserves the right to substitute product that may vary in species, core, country of origin, and/or other specifications.